



批次	样品名称	生产 日期	分析结果			
			Pb%	Cu%	Ag(g/t)	Au(g/t)
F-22-11-28	浮渣熔炼炉高冰铜	11.29	12.76	47.22	1965	5.00
F-22-12-1	浮渣熔炼炉高冰铜	12.02	10.19	48.80	2149	4.80
F-22-12-4	浮渣熔炼炉高冰铜	12.05	11.35	50.39	2115	4.00
F-22-12-6	浮渣熔炼炉高冰铜	12.07	11.77	51.40	1823	4.60
F-22-12-8	浮渣熔炼炉高冰铜	12.09	11.09	50.86	2050	5.40

