



批次	样品名称	生产 日期	分析结果			
			Pb%	Cu%	Ag(g/t)	Au(g/t)
F-22-11-24	浮渣熔炼炉低冰铜	11.25	3.03	20.14	250	0.00
F-22-11-25	浮渣熔炼炉低冰铜	11.26	3.76	27.00	428	0.00
F-22-11-26	浮渣熔炼炉低冰铜	11.27	1.07	20.28	310	0.00
F-22-11-28	浮渣熔炼炉低冰铜	11.29	4.96	24.75	431	0.00
F-22-12-2	浮渣熔炼炉低冰铜	12.03	3.37	25.41	526	0.00
F-22-12-5	浮渣熔炼炉低冰铜	12.06	5.90	28.36	638	0.00
F-22-12-7	浮渣熔炼炉低冰铜	12.08	4.29	29.05	459	0.00

